

**PRODUCTION OF FLY ASH-BASED GEOPOLYMER BRICKS THROUGH
GEOLYMERIZATION PROCESS**

WAN MASTURA BINTI WAN IBRAHIM

© This item is protected by original copyright

UNIVERSITI MALAYSIA PERLIS

2013



**PRODUCTION OF FLY ASH-BASED
GEOPOLYMER BRICKS THROUGH
GEOPOLYMERIZATION PROCESS**

by

**WAN MASTURA BINTI WAN IBRAHIM
(1030410550)**

A Thesis Submitted in Fulfillment of the requirements for the degree of
Master of Science (Materials Engineering)

**School of Materials Engineering
UNIVERSITI MALAYSIA PERLIS
2013**

APPROVAL AND DECLARATION SHEET

This thesis titled Production of fly ash-based geopolymer bricks through geopolymerization process was prepared and submitted by Wan Mastura Binti Wan Ibrahim (Matrix Number: 1030410550) and has been found satisfactory in terms of scope, quality and presentation as partial fulfillment of the requirement for the award of degree of Master of Science (Materials Engineering) in University Malaysia Perlis (UniMAP).

Check and Approved by

.....
(BRIG. JEN. DATO' PROF. DR. KAMARUDIN HUSIN)

Project Supervisor

School of Materials Engineering

Universiti Malaysia Perlis

(Date:)

School of Materials Engineering

Universiti Malaysia Perlis

2013

ACKNOWLEDGEMENT

Praise be to Allah, the Lord of Universe

First and foremost, al-Hamdulillah, I am very grateful to Allah S.W.T. for giving me strength, confidence and patience to endure all the problems and obstacles and finally complete this study successfully. My heartfelt thanks and appreciation goes to my project supervisor, Brig. Jen. Dato' Prof. Dr. Kamarudin Husin and my co-supervisor, Associate Professor Dr. Khairul Nizar Ismail for their continuous guidance, endless patience, great concern, invaluable assistance, useful advice and encouragement from the very beginning to the end of this period.

A lot of thanks to Mr. Mohd Mustafa Al Bakri Abdullah, my project leader of Center of Excellence Geopolymer and Green Technology (CEGeoGTech), UniMAP, for his continuous assistance, uncountable help and guidance, throughout the whole process to complete my research. My gratitude is also extended to Mr. Nasir, Mr. Hadzrul, Mr. Azmi Aziz and Mr. Wan Arif, technician and lecturer of School of Materials Engineering, UniMAP, for assisting in putting my research study into action and for their help and guidance during laboratory works.

I would like to express my gratitude to my mum and lovely family for being very supportive and encouraging from the very beginning. Their prayers, strength and love have guided me through thick and thin. Without their support and tolerance, it would never have been possible.

Lastly my sincere appreciation also extends to my friends at CEGeoGTech, School of materials Engineering, thanks for everything. Also, to those who have helped directly or indirectly, I wish I could have put their names here, thanks for being helpful, cooperative and supportive. Only Allah could pay your kindness. Thank you very much.

TABLE OF CONTENTS

	PAGES
THESIS DECLARATION	ii
ACKNOWLEDGEMENT	iii
TABLE OF CONTENTS	iv
LIST OF TABLES	viii
LIST OF FIGURES	ix
LIST OF ABBREVIATIONS, SYMBOLS & CHARACTERS	xii
ABSTRAK	xiv
ABSTRACT	xv
CHAPTER 1 INTRODUCTION	
1.1 Research Background	1
1.2 Problem Statement	3
1.3 Research Aim and Objectives	4
1.4 Research Scope	5
1.5 Thesis Outline	5
CHAPTER 2 LITERATURE REVIEW	
2.1 Introduction	7
2.2 Type of Bricks	8
2.2.1 Clay Bricks	8
2.2.2 Calcium Silicate Bricks	11
2.2.3 Concrete Bricks	12
2.2.4 Cement Bricks	14
2.3 Classification of Bricks	16
2.3.1 Building Bricks	16
2.3.2 Facing Bricks	16

2.3.3 Engineering Bricks	17
2.4 Fly Ash	18
2.5 The Use of Fly Ash in Brick	20
2.6 Geopolymers	22
2.6.1 Geopolymerization	25
2.6.2 Geopolymer Bricks	29

CHAPTER 3 RESEARCH METHODOLOGY

3.1 Introduction	32
3.2 Experimental Program	33
3.3 Required Materials	35
3.3.1 Fly Ash	35
3.3.2 Alkaline Liquid	36
3.3.3 Sand	38
3.4 Parameter Used for Fly Ash-Based Geopolymer Bricks	39
3.4.1 Mix Detail for Fly Ash-To-Sand Ratio	39
3.5 Mixture Proportion	40
3.6 Specimen Preparation	41
3.6.1 Mixing Process	43
3.6.2 Curing Process	44
3.7 Testing Program	45
3.7.1 Compressive Strength Test	45
3.7.2 Water Absorption Test	47
3.7.3 Dimension Test	48
3.7.4 Density Analysis	51
3.7.5 Microstructural Characterisation	51
3.7.5.1 Scanning Electron Microscopy (SEM)	51
3.7.5.2 X-Ray Diffraction (XRD)	52

CHAPTER 4 RESULTS AND DISCUSSION

4.1 Introduction	53
4.2 Effect of Salient Parameters	54
4.2.1 Ratio of Fly Ash-To-Sand	54
4.2.2 Curing Time	56
4.2.3 Curing Temperature	58
4.3 Compressive Strength	61
4.4 Water Absorption	63
4.5 The Mode Failure of Fly Ash-Based Geopolymer Bricks	64
4.6 Dimensional Tolerances	67
4.7 Density Analysis	68
4.8 Microstructure of Fly Ash-Based Geopolymer Bricks	70
4.8.1 Scanning Electron Microscope (SEM)	70
4.8.2 X-Ray Diffraction (XRD)	75

CHAPTER 5 CONCLUSIONS AND RECOMMENDATIONS

5.1 Conclusions	78
5.1.1 Production of Fly Ash-Based Geopolymer Bricks	78
5.1.2 Physical and Mechanical Properties of Geopolymer Bricks	79
5.1.3 Microstructural Character of Geopolymer Bricks	80
5.1.4 Overall Conclusions	81
5.2 Recommendations	82

REFERENCES	83
------------	----

APPENDIX A	90
APPENDIX B	92
APPENDIX C	99
LIST OF PUBLICATIONS	102

© This item is protected by original copyright

LIST OF TABLES

TABLE NO.		PAGE
2.1	Sizes of Bricks, BS 3921: 1985	9
2.2	Classes of Calcium Silicate Bricks, BS 187: 1978	11
2.3	Strength, absorption and density classification of concrete building bricks (ASTM C55, 2011)	13
2.4	Compressive strength report of cement bricks	15
2.5	Classification of Bricks by Compressive Strength and Water Absorption, BS 3921: 1985	17
2.6	Specifications for Fly Ash according to ASTM C618-12 Standard	19
2.7	Applications of Geopolymer Material	25
3.1	Chemical composition of fly ash	36
3.2	Mix design details for various ratios of fly ash: sand	40
3.3	Size of bricks	41
3.4	Limits of bricks dimensions recommended by BS 3921:1985	50
4.1	Properties of geopolymer bricks compared to common bricks used in Malaysia	63
4.2	Dimensions of bricks measured	68
4.3	Density of geopolymer bricks measured	69

LIST OF FIGURES

FIGURE NO.		PAGE
2.1	The difference between working and coordinating size	10
2.2	Clay bricks	10
2.3	Calcium Silicate bricks	12
2.4	Concrete Bricks	13
2.5	Cement Bricks	15
2.6	Schematic outline of the reaction processes involved in geopolymerisation (Van Deynter, et. al., 2007)	26
2.7	Descriptive model of the alkali activation of fly ash (Pacheco-Torgal, et. al., 2008)	27
3.1	Sequences of research laboratory work	33
3.2	Flow chart for production of geopolymer bricks	34
3.3	SEM image of Fly Ash	35
3.4	Sodium hydroxide (NaOH) solutions	37
3.5	Sodium silicate (Na ₂ SiO ₃) solutions	38
3.6	Measurement the size of bricks	42
3.7	Machine and mould for making bricks	42
3.8	Pan Mixer Used for Manufacturing Geopolymer Bricks	44
3.9	Mixing Sequence	44
3.10	Curing process	45
3.11	Brick tested on stretcher face	47

3.12	Overall measurement of (a) length, (b) height and (c) width for 24 bricks	50
4.1	Compressive strength of different ratio fly ash-to-sand	55
4.2	Water absorption of different ratio fly ash-to-sand	56
4.3	Compressive strength of different curing time	57
4.4	Water absorption of different curing time	58
4.5	Compressive strength of different curing temperature	59
4.6	Water absorption of different curing temperature	60
4.7	Compressive strength of different aging time	62
4.8	Water absorption of different aging time	64
4.9	Common failure pattern for 1 days of ageing	65
4.10	Common failure pattern for 3 days of ageing	65
4.11	Common failure pattern for 7 days of ageing	66
4.12	Common failure pattern for 28 days of ageing	66
4.13	Common failure pattern for 60 days of ageing	67
4.14	Relation of density and compressive strength of geopolymer bricks	70
4.15	SEM micrograph of class F fly ash with amplify x 5000 magnifications	71
4.16	SEM micrograph of geopolymer bricks cured at room temperature for 24 hours x 2000 magnifications	72
4.17	SEM micrograph of geopolymer bricks cured at 70°C for 24 hours x 2000 magnifications	73
4.18	SEM micrograph of geopolymer bricks at 7 days of ageing x 2000 magnifications	74

4.19	SEM micrograph of geopolymer bricks at 60 days of ageing x 2000 magnifications	74
4.20	Diffractograms for geopolymer bricks and original fly ash	77

© This item is protected by original copyright

LIST OF ABBREVIATIONS, SYMBOLS AND CHARACTERS

ASTM	-	American Society for Testing and Materials
Si	-	Silica
Al	-	Alumina
O	-	Oxygen
XRD	-	X-Ray Diffraction
SEM	-	Scanning Electron Microscopy
BS	-	British Standard
FBS	-	Face Brick Standard
FBX	-	Face Brick Extra
FBA	-	Face Brick Aesthetic
Fe	-	Iron
Ti	-	Titanium
P	-	Phosphorus
S	-	Sulfur
Mg	-	Magnesium
Cl	-	Chlorine
K	-	Potassium
Ca	-	Calcium
Zn	-	Zinc
Sr	-	Strontium
XRF	-	X-Ray Fluorescence
CaO	-	Calcium Oxide
NaOH	-	Sodium Hydroxide

Na_2SiO_3	-	Sodium Silicate
MPa	-	Megapascal
EPA	-	Environmental Protection Agency
TCLP	-	Toxicity Characteristic Leaching Procedure
CO_2	-	Carbon Dioxide
SiO_4	-	Silicate
AlO_4	-	Aluminates
OPC	-	Ordinary Portland Cement
3D	-	Three Dimensional
LTGS	-	Low Temperature Geopolymeric Setting
CEGeoGTech	-	Center of Excellence Geopolymer and Green Technology
SPCI	-	South Pacific Chemicals Industries
M	-	Molar ratio
mm	-	Millimeter

© This item is protected by original copyright

Pengeluaran Bata Geopolimer Berasaskan Abu Terbang (Fly Ash) Melalui Proses Pengeopolimeran

ABSTRAK

Penggunaan abu terbang (fly ash) sebagai bahan mentah untuk membuat bata geopolimer telah menjadi satu penyelesaian yang baik iaitu dapat memulihara sumber asli, mengurangkan pencemaran dan mengekalkan persekitaran. Geopolimer berasaskan abu terbang (fly ash) telah dikaji oleh beberapa penyelidik di seluruh dunia bagi beberapa dekad dahulu disebabkan oleh sifat-sifat mekanikalnya yang bagus. Geopolimer adalah sejenis bahan amorfus silikat alumina yang boleh disintesis daripada tindakbalas polikondensasi antara bahan geopolimerik dan larutan alkali. Kajian ini telah dijalankan untuk menghasilkan bata geopolimer berasaskan abu terbang (fly ash) dengan cara pembentukan melalui tekanan tanpa prosedur membakar dan juga penggunaan tenaga yang rendah. Eksperimen ini telah dijalankan ke atas bata geopolimer berasaskan abu terbang (fly ash) dengan mengubah nisbah abu terbang kepada pasir (1:2 - 1:5, oleh jisim nisbah), masa pematangan (1 - 24 jam) dan suhu pematangan (suhu bilik – 80 °C). Kekuatan mampatan, penyerapan air, ujian dimensi dan analisis ketumpatan telah ditetapkan sebagai sifat-sifat mekanikal yang perlu diuji ke atas bata geopolimer berasaskan abu terbang (fly ash). Ujian mampatan dan ujian penyerapan air telah diukur pada 1, 3, 7, 28 dan 60 hari. Hasil siasatan menunjukkan bahawa kekuatan mampatan semakin berkurang apabila nisbah abu terbang kepada pasir meningkat. Walau bagaimanapun, kekuatan mampatan meningkat dengan peningkatan dalam masa pematangan dan suhu pematangan. Kekuatan mampatan sehingga 24.3 MPa telah diperolehi pada suhu pematangan 70 °C bagi tempoh 24 jam masa pematangan pada hari ke-60. Ketumpatan bata geopolimer berkisar antara 1800 Kg/m³ sehingga 1950 Kg/m³. Sifat mikrostruktur bata geopolimer berasaskan abu terbang (fly ash) telah disiasat dengan menggunakan analisis XRD dan SEM.

Production of Fly Ash-Based Geopolymer Bricks Through Geopolymerization Process

ABSTRACT

Utilization of fly ash as a raw material for geopolymer brick production seems to be a logical solution that allows for the conservation of natural resources, abates further pollution and preserves the environment. Fly ash-based geopolymer have been studied by several researchers worldwide for several decades due to their excellent mechanical properties. Geopolymer is a type of amorphous alumino-silicate material which can be synthesized by polycondensation reaction of geopolymeric materials, and alkali solutions. This study has been conducted to produce fly ash-based geopolymer bricks by means of pressure forming without firing procedure and low energy consumptions. The experiments were conducted on fly ash-based geopolymer bricks by varying the ratio of fly ash-to-sand (1:2 - 1:5, by mass of ratio), curing time (1 - 24 hours) and curing temperature (room temperature - 80°C). Compressive strength, water absorption, dimensional test and density analysis was set as the mechanical properties to be tested on the fly ash-based geopolymer bricks. The compression test and water absorption test were measured at 1, 3, 7, 28 and 60 days. Results of the investigation indicated that there was decrease in compressive strength when the ratio of fly ash-to-sand increase. However, the strength was increased with increase in curing time and curing temperature. Compressive strength up to 20.3 MPa was obtained with curing at 70 °C for a period of 24 hours at 60 days of ageing. The density of geopolymer bricks ranged between 1800 Kg/m³ to 1950 Kg/m³. The microstructural properties of fly ash-based geopolymer bricks were investigated by using XRD and SEM analysis.

CHAPTER 1

INTRODUCTION

1.1 Research Background

Bricks are considered to be one of the oldest and the most environmentally friendly building materials. Bricks are usually used in the construction of buildings as building wall, paving and flooring. Bricks are made from variety of materials like calcium silicate and concrete and bricks made from clay are the most common. However, production of clay bricks requires high temperature (900-1000°C) kiln firing and also releases substantial quantity of greenhouse gases (Ahmari & Zhang, 2012). Due to this problem, some researchers start to use other source materials to produce construction and building bricks. One of the most popular new bricks is ‘fly ash brick’ and also known as ‘greenest brick’. Uses of fly ash in making bricks have many advantages over conventional clay bricks as they are does not emit any pollutant and greenhouse gas during and after manufacturing, requires much less energy consumption, and it costs about 20% less than manufacturing clay bricks (Kayali, 2005).

Fly ash is a fine particulate material separated from the flue gas of coal-fired power stations which rich in alumina and silica. As the production of fly ash rising continuously and creating serious environmental pollution problems, these should not be disposed simply to prevent environmental pollution, but should be treated as a valuable resources or reuse as raw material in new technology with good properties.

American Society for Testing and Materials (ASTM) international standards classifies two class of fly ash which is class F (Low calcium) and class C (High calcium) (ASTM C 618, 2008). Class F fly ash has considerable as pozzolanic materials or pozzolans and can be activated by high alkaline solutions to act as a binder through chemical polymerization reactions (Swanepoel & Strydom, 2002). This reaction will transformed aluminosilicate materials (fly ash) into aluminosilicate polymers which are also known as geopolymers.

Geopolymer is one of new material and have been investigated, studied, and utilized for some decades by several researchers throughout the world. Geopolymer was first developed by Prof. Joseph Davidovits in St. Quentin, France, in the 1970s (Davidovits, 1989). The main properties of geopolymers are high compressive strength, low shrinkage, fast or slow setting, acid resistance, fire resistance and low thermal conductivity depending on the raw material used and processing conditions (Duxson, et al., 2007). The geopolymer-based material involves chemical reaction known as geopolymerization process yields polymeric Si – O – Al bonds. The geopolymerization process involves a substantially fast chemical reaction under alkaline solutions on silica-alumina materials that results in a three-dimensional polymeric chain and ring structure. Much research has been studied in utilization of fly ash as source material in making of geopolymer materials. However, there is limited information that can be found in the literature regarding using the geopolymer technology to make fly ash-based geopolymer brick.

Modern application of fly ash-based geopolymer material is focused on high performance which better and more reliable quality, improved durability and high strength construction material. The development fly ash-based geopolymer brick for construction application is still at early stage. Therefore, a lot of further research on this

type of brick technology needs to be carried out to enhance the quality in constructing building and other infrastructures. Compare to conventional brick used in Malaysia, fly ash-based geopolymer brick are low cost and uses of fly ash as source material in brick production can reduce the effect of environmental problems.

This research presents a design and performance evaluation of fly ash-based geopolymer brick. It proposes new technology of brick production in Malaysia and widening the possibilities to recycle waste (fly ash) to useful products especially building materials which can contribute to the environmental and economical benefits. The ultimate goal of this research is to measure, evaluate as well as to compare the performance of fly ash-based geopolymer bricks with common bricks in Malaysia based on the result obtain through this research. The performance of geopolymer brick is measured based on engineering properties present from the brick which are compressive strength, water absorption, and density. The use of fly ash-based geopolymer brick in construction application is possible but requires more research and development in the future.

1.2 Problem Statement

The main objective of this study is to create new materials to produce bricks in a way that benefits the community, the environment and industry. To achieve this, the preservation of natural resources or waste materials could be an alternative solution for progressively elimination waste and produces environmental friendly construction materials, while reducing the rate of ashes been disposed in landfill.

Every year, millions of tons of fly ash are generated from thermal power stations as well as the petrochemical industry all over the world. The abundance availability of fly ash has creating problems in disposal operations and tremendous environmental

concerns. For this reason, utilization of this waste material will be beneficial when treated as valuable resource in production of good quality building materials. Brick technologists are gradually finding applications in using of fly ash as a raw material for producing greenest brick which are free from environmental pollution. Comprehensive utilization of fly ash in production of geopolymer brick which is a kind of green material contributes to social benefits and economic benefits advance together, as well as to the development of new brick with better performances.

For the above mentioned reasons, present research will be carried out to determine and understand the suitability uses of fly ash for production of geopolymer bricks and their performances as compared to common bricks used in Malaysia.

1.3 Research Aim and Objectives

The aim of the research is to develop fly ash geopolymer bricks by using geopolymerization process. This objective of this research can be summarized as follows:-

- 1) To produce the optimum mix proportion for processing fly ash-based geopolymer bricks
- 2) To identify the factors and parameters, which affect the performances of fly ash geopolymer bricks
- 3) To investigate the mechanical and microstructural properties of fly ash-based geopolymer bricks

1.4 Research Scope

The scope of study for this research basically to produce and study the properties of fly ash geopolymer bricks. The class F fly ash was come from the power plant Manjung, Perak, Malaysia. This study includes lab works and lab testing on fly ash geopolymer bricks. The entire tests conducted are in accordance to the standard which is American Society Testing Method and British Standard. The mechanical properties to be studied are focused on the compressive strength, density analysis, water absorption test, and dimension test. X-ray diffraction (XRD) and scanning electron microscopy (SEM) analysis was performed to investigate the microstructure properties of fly ash geopolymer bricks.

1.5 Thesis Outline

The thesis is divided into five chapters. Chapter 1 introduces the research background, aims and objectives of research, research scope, problem statement, research overview and the outline of the thesis.

Chapter 2 discusses about the literature review based on the geopolymer technology and potential use of fly ash in production of environmental friendly brick. The literature review is focused on geopolymer performance, types of experiment carried out by several researcher and application of geopolymer materials.

Chapter 3 explains the details of the materials and the methodologist implemented in the research to develop the mixture proportions, the mixing process and the curing process of geopolymer bricks. This chapter also describes the mechanical and microstructural tests of geopolymer bricks according to the ASTM and BS standard.

Chapter 4 presents the test results and discusses the findings of experimental program. The properties and effect of several factors affecting the performance of geopolymer bricks were also discussed in this chapter.

Chapter 5 states the conclusions of this study and some recommendations for the future work. The thesis ends with a Reference List and several Appendices.

© This item is protected by original copyright

CHAPTER 2

LITERATURE REVIEW

2.1 Introduction

The history of civilization is synonymous to the history of masonry. Man's first civilization, which started about 6000 years ago, was evident from the remains of the Mesopotamians masonry heritage. During those days masonry buildings were constructed from any available material at hand. For example, the Mesopotamians used bricks, made from alluvial deposits of the nearby River Euphrates and Tigris to build their cities beside two rivers. The Egyptian Pyramids that existed along the rocky borders of the Nile valley were examples of such stone masonry. The early forms of masonry application in Malaysia dated back about 350 years ago with the construction of the Stadthuys in Malacca, built by the Dutch in 1650. At that time, brickwork buildings were built especially for government offices, quarters and residential homes. The administrative block, Sultan Abdul Samad building built in 1894 and given a face-lift during the Fourth Malaysia Plan (1981 - 1985) is an example of a masonry heritage, which stands as a remarkable landmark of Kuala Lumpur (Zainab, 2005).

A brick is a block of ceramic material used in masonry construction, usually laid using mortar. Bricks may be made from clay, shale, soft slate, calcium silicate, concrete, or shaped from quarried stone. Brick is still used until today because of its own characteristics and due to its values and advantages. Uses of brick in the field of

construction are very broad. For example, bricks can be used as internal and external wall, facing wall, earth retaining wall, and sewerage work.

This chapter presents a short review of bricks available in the market and their specifications. This will be followed by the review on the background of geopolymer technology, including the reaction involves in geopolymer. The rest of chapter includes the engineering properties of bricks in terms of compressive strength, water absorption, dimension tolerances and density of the bricks.

2.2 Type of Bricks

In the market, there are numerous types of bricks that can be found and being used in the construction industry. The types of bricks were classified according to the material and method used for making those different types of bricks. There are four commonly used bricks types which are clay bricks, calcium silicate bricks, concrete bricks and cement brick. These types of bricks had been standardized for its usage.

2.2.1 Clay Bricks

Clay brick is the most extensively used type of masonry units throughout the world. Its widespread use is mainly due to the availability of clay and shale in most countries. Clay bricks are made by shaping suitable clays to units of standard size, which are then fired to a temperature in range 900°C to 1200°C (Brick Industry Association, 2006). In Malaysia, clay brick is commonly used in construction based on the British Standard BS 3921: 1985, standard for specification of clay bricks. By referring to BS 3921: 1985, the work size of clay brick is 215 mm x 102.5 mm x 65 mm while the coordination size of clay brick had been set to 225 mm x 112.5 mm x 75 mm.