



**Waste Seashell as Calcium Oxide Catalyst for Bio-oil
Production From Empty Fruit Bunch**

By

Nurfatirah Binti Nordin

(1331110823)

A thesis submitted in fulfillment of the requirements for the degree of
Master of Science in Bioprocess Engineering

**School of Bioprocess Engineering
UNIVERSITI MALAYSIA PERLIS**

2017

ACKNOWLEDGEMENT

I gratefully acknowledge and thank my supervisor Assoc. Prof. Dr Zainab Hamzah for her helpful guidance, advice and encouragement throughout this work. I am also very grateful to my co-supervisor Dr Farizul Hafiz Kassim for advice and guidance in making this research possible. Their enthusiasm and expertise inspired my work and guidance, suggestions and patience are greatly appreciated.

It is also my pleasure to express my gratitude to the staffs of School of Bioprocess Engineering, School of Environmental Engineering, School of Material Engineering, School of Manufacture Engineering and School of Mechanical Engineering, University Malaysia Perlis (UniMAP), especially the teaching engineers and technicians for their tremendous help in analyses, equipment trouble-shooting, and other lab work. Not to forget, my gratitude to Assoc. Prof. Dr Othman and Dr Alina Rahayu Mohamed for the support and advice.

I would like to extend my heartfelt thanks to Higher Education Ministry of Malaysia for the financial support given under Malaysia Technical University Network (MTUN) (9016-00005), Long Term Research Grant (LRGS) (9012 00004) and MyBrain 15 (MyMaster).

Last but not least, I would like to express my utmost gratitude to my beloved parents, Mr Nordin and Mrs Timah, my grandmother, members of my family and my cute nephew and nieces, Acha, Akil and Aishah for their love, patience and continuous support. Finally, I would like to thank all my postgraduate friends and my friends for all the support and friendships. Without their presence, the journey of finishing my project would be very challenging.

TABLE OF CONTENTS

THESIS OF DECLARATION	i
ACKNOWLEDGEMENT	ii
TABLE OF CONTENTS	iii
LIST OF TABLE	viii
LIST OF FIGURES	x
LIST OF SYMBOLS	xii
LIST OF ABBREVIATIONS	xiii
ABSTRAK	xvi
ABSTRACT	xvii
CHAPTER 1	1
1.1 Background of Study	1
1.2 Problem Statement	2
1.3 Objective of the Study	2
1.4 Hypothesis	3
1.5 Scope of the Study	3
CHAPTER 2	5
2.1 Pyrolysis	5

2.1.1 Different Types of Pyrolysis	6
2.2 Pyrolysis Reaction	7
2.3 Non-catalytic Pyrolysis	10
2.4 Catalytic Pyrolysis	11
2.5 Pyrolysis Parameters	16
2.5.1 Effect of Temperature	16
2.5.2 Effect of Particle Size	18
2.5.3 Effect of Nitrogen Flow Rate	20
2.5.4 Reactor	22
2.6 Pyrolysis Products	26
2.6.1 Bio-oil	26
2.6.2 Biochar	28
2.6.3 Gas	29
2.7 Lignocellulose of Biomass	30
2.7.1 General Background of Empty Fruit Bunch (EFB)	33
2.7.2 Pyrolysis of EFB	34
2.7.3 Composition and Characteristic of EFB	36
2.8 Calcium Oxide Catalyst	37
2.8.1 Source of Calcium Oxide	37
2.8.2 Activity of CaO in Pyrolysis	39

2.9 Zinc Oxide (ZnO) as Catalyst in Pyrolysis	41
2.10 Design of Experiment (DoE)	41
2.10.1 Response Surface Methodology (RSM)	42
2.10.2 Central Composite Design (CCD)	43
CHAPTER 3	45
3.1 Materials	45
3.1.1 Empty Fruit Bunch (EFB)	46
3.1.2 Waste seashells	47
3.1.3 Zinc Oxide	47
3.2 Pyrolysis	48
3.3 Optimization by Central Composite Design (CCD)	49
3.4 Catalytic Pyrolysis	52
3.6 Characterization of Catalyst	52
3.7 Characterization of Pyrolytic Bio-Oil	52
3.7.1 Viscosity	53
3.7.2 pH Analysis	53
3.7.3 Functional Group using FTIR Analysis	53
3.7.4 GC-MS Analysis	54
CHAPTER 4	57
4.1 Characterization of the EFB	57

4.2 Optimization of Pyrolysis Process of EFB	58
4.2.1 Regression Analysis in Central Composite Design	58
4.2.2 Effect of Operating Variables on Bio-Oil Products using Response Surface Methodology	62
4.2.4 Optimization for Bio-oil Production	66
4.3 Elemental Composition and Properties of Catalyst	68
4.4 Effect of Calcined Seashell Catalyst on the Distribution of Pyrolysis Products	71
4.4.1 Effect of ZnO Commercial Catalyst on Product Yield	73
4.5 Characterization	74
4.5.1 Physical and Chemical Properties of Bio-Oil	74
4.5.2 Determination of Functional Groups and Organic Compounds Present in Bio-oil using Fourier Transform Infrared (FTIR) and Gas Chromatography/Mass Spectrometry (GC/MS) Analysis	76
4.5.2.1 Determination of Functional Groups using FTIR	76
4.5.2.1 Determination of Organic Compounds using GC-MS Technique	78
CHAPTER 5	83
5.1 Conclusions	83
5.2 RECOMMENDATIONS	85
REFERENCES	86
APPENDIX A	95

APPENDIX B	96
APPENDIX C	98
APPENDIX D	99
LIST OF PUBLICATIONS	100
LIST OF AWARDS	102

©This item is protected by original copyright

LIST OF TABLE

NO	PAGE
2.1 Characteristic of various type of pyrolysis (Marshall, 2013)	7
2.2 Different raw materials investigated in pyrolysis of biomass	11
2.3 Different types of catalysts used in pyrolysis biomass for bio-oil production	12
2.4 Different pyrolysis temperature for various type of biomass	18
2.5 Bio-oil yield from different raw material with various range of particle size	20
2.6 Bio-oil yield from different raw material with various range of nitrogen flow rate	21
2.7 Advantages, disadvantages, and bio-oil yield of different pyrolysis reactor (Rasul & Jahirul, 2012)	24
2.8 Physical properties of typical bio-oil and heavy fuel oil (Marshall, 2013)	27
2.9 EFB as raw material for pyrolysis biomass	35
2.10 Properties of EFB (Abdullah et al., 2013; Rohim et al., 2014)	37
2.11 Catalytic pyrolysis using CaO as catalyst	40
3.1 Independent variables in central composite design (CCD) study	50
3.2 Sequence of experiments for CCD	51

4.1 Proximate and ultimate analysis of EFB	58
4.2 Results of bio-oil yield from pyrolysis of EFB	59
4.3 Analysis of variance (ANOVA) for response surface quadratic model	61
4.4 Optimal design for bio-oil yield from EFB pyrolysis	67
4.5 Result of model validation at optimum condition	68
4.6 EDX analysis of calcined seashell catalyst	70
4.7 Chemical compounds of calcined waste seashell catalyst	70
4.8 Physical and chemical properties of bio-oil with and without addition catalyst	74
4.9 FTIR functional group composition of pyrolysis liquids	78
4.10 Relative proportions (area) of similar main pyrolysis compounds in bio-oils	80

LIST OF FIGURES

NO	PAGE
2. 1 TG and DTG profile of EFB (Ninduangdee et al., 2015)	9
2.2 A representative lignin pyrolysis reactions for synthesis of aromatics over a typical base catalyst.	14
2.3 Applications of pyrolysis bio-oil (Xiu & Shahbazi, 2012; Marshall, 2013)	27
2.4 Chemical structure of hemicelluloses (Chen et al. 2014)	31
2.5 Chemical structure of cellulose (Zhen, 2013)	31
2. 6 Chemical structure of lignin (Sara, 2009)	32
2. 7 Layout of the CCD of 3 variables at 5 level (Myers, 1976)	44
3.1 (a) EFB (b) Waste seashell (c) Zinc oxide (d) Nitrogen gas cylinder	46
3.2 Fixed bed reactor system	48
3.3 Flow chart of the first part of the study for EFB and catalyst	55
3. 4 Flow chart of the second main study	56
4.1 3D surface plot showing the effect of particle size and pyrolysis temperature	64
4 2 3D surface plot showing the effect of nitrogen flow rate and pyrolysis temperature	65
4.3 The 3D surface plot showing the effect of nitrogen flow rate and particle size	66

4.4 SEM image of waste seashell (a) raw waste seashell and (b) calcined waste seashell catalyst under inert atmosphere at 800°C	69
4.5 The effect of the calcined seashell catalyst addition on the distribution of pyrolysis product yields at 250cc/min, 628°C and 710-1000µm	72
4.6 The effect of the ZnO catalyst addition on the distribution of pyrolysis product yields at at 250cc/min, 628°C and 710-1000µm	74
4.7 FTIR spectra of samples (a) non-catalytic pyrolysis of bio-oil (b) catalytic pyrolysis of bio-oil	77

LIST OF SYMBOLS

SYMBOLS

α	Alpha (axial distance from centre point which makes the design rotatable)
β_0	regression coefficients for the intercept coefficient
β_i	regression coefficients for the linear coefficient
β_{ii}	regression coefficients for the quadratic coefficient
β_{ij}	regression coefficients for the interaction coefficient
$^{\circ}\text{C}$	degree Celsius
σ	standard deviation
χ^i, χ_j	coded independent variables
ε	residual associated to the experiments
μm	micrometer
cc/min	cubic centimeter per minute
$^{\circ}\text{C}/\text{min}$	degree celcius per minute
$\text{m}^2 \text{g}^{-1}$	meter squared per gram
cm^3/g	cubic centimeter per gram
cP	centipoise
cm^{-1}	reciprocal centimeter or wavenumber
$^{\circ}\text{C}/\text{s}$	degree Celsius per second
ml/min	militer per minute
MJ/Kg	megajoule per kilogram
g	gram
mm	millimeter

LIST OF ABBREVIATIONS

CCD	Central Composite Design
ANOVA	Analysis of Variance
RSM	Response Surface Methodology
DoE	Design of Experiment
OFAT	One Factor At One Time
Y	Response Parameter
A	Independence variable (Particle Size)
B	Independence variable (Pyrolysis Temperature)
C	Independence variable (Nitrogen Flow Rate)
ASTM	American Standard Test Method
NIST	National Institute of Standards and Technology (NIST)
JCPDS	Joint Committee on Powder Diffraction Standards
CHNOS	Carbon Hydrogen Nitrogen Oxygen Sulfur Analyzer
TGA	Thermo Gravimetric Analysis
SEM	Scanning Electron Microscope
EDX	Energy Dispersive X-ray
XRD	X-Ray Diffraction
XRF	X-Ray Fluorescence
BET	Brunauer-Emmett-Teller
FTIR	Fourier Transform Infrared
GC-MS	Gas Chromatography Mass Spectrometry
HPLC	High Performance Liquid Chromatography
GPC	Gel Permeation Chromatography

LHV	Lower Heating Value
EFB	Empty Fruit Bunch
ZnO	Zinc Oxide
CaO	Calcium Oxide
CaCO ₃	Calcium Carbonate
CO ₂	Carbon Dioxide
CO	Carbon Monoxide
CH ₄	Methane
Ca	Calcium
C	Carbon
O	Oxygen
Mg	Magnesium
K	Potassium
N	Nitrogen
PAHs	Polycyclic Aromatic Hydrocarbons
Na ₂ O	Sodium Oxide
TiO ₂	Titanium Dioxide
Fe ₂ O ₃	Iron (III) Oxide
CuO	Copper (II) Oxide
SrO	Strontium Oxide
RuO ₂	Ruthenium (IV) Oxide
CeO ₂	Cerium (IV) Oxide
Tm ₂ O ₃	Thulium (III) Oxide
Lu ₂ O ₃	Lutetium (III) Oxide
Co ₃ O ₄	Cobalt (II) Dicobalt(III) Oxide

BaO	Barium Oxide
Al ₂ O ₃	Aluminum Oxide
Cr ₂ O ₃	Chromium (III) Oxide
H ₂ S	Hydrogen Sulfide
HCN	Hydrogen Cyanide

©This item is protected by original copyright

Sisa Kulit Kerang sebagai Pemangkin Kalsium Oksida untuk Penghasilan Minyak-bio daripada Tanda Kosong Buah Kelapa Sawit (TKBKS)

ABSTRAK

Sisa kelapa sawit boleh dijadikan minyak-bio melalui proses pirolisis kerana ianya merupakan sumber boleh diperbaharui bagi memastikan kesinambungan dan keupayaan untuk penyelesaian tenaga boleh diperbaharui. Ia adalah satu cabaran besar untuk menukarkan tandan kosong buah kelapa sawit (TKBKS) ke dalam bentuk produk minyak-bio dengan cara yang berkesan. Di samping itu, pemangkin digunakan dalam proses pirolisis untuk menilai kesan pemangkin dalam pirolisis proses TBKKS terhadap pengagihan minyak-bio, bioarang dan gas sebagai produk akhir yang terhasil. Oleh itu, kajian ini dijalankan untuk menilai kesan pemangkin kalsium oksida berasaskan sisa kulit kerang dengan menggunakan reaktor lapisan padat untuk penghasilan minyak-bio daripada TKBKS. Pengoptimuman parameter proses pirolisis seperti saiz zarah (A), suhu pirolisis (B) dan kadar aliran nitrogen (C) telah dikaji melalui reka bentuk komposit pusat dengan minyak-bio dianggap sebagai respon. Suhu pirolisis (B) telah dianggap sebagai parameter yang paling penting diikuti saiz zarah (A). Keadaan yang optimum pada suhu pirolisis 628°C, kadar aliran nitrogen 250 ml/min dan julat saiz zarah 710-1000 μ m menghasilkan minyak-bio sebanyak 44.1%. Kesan pemangkin dalam proses pirolisis telah dijalankan pada keadaan optimum 5 % menghasilkan minyak-bio sebanyak 44.5%. Keputusan analisa kumpulan berfungsi menunjukkan kehadiran asid, keton, hidrokarbon aromatik polisiklik alkohol dan kumpulan karbonil. Nilai pH yang diperolehi oleh minyak-bio daripada pirolisis berpemangkin adalah lebih tinggi (pH 4.3) berbanding dengan minyak-bio daripada pirolisis tanpa pemangkin (pH 3.5). Oleh itu, keasidan minyak-bio telah dikurangkan oleh kalsium oksida pemangkin dari sisa kulit kerang. Kesan kelikatan minyak-bio diperolehi dengan menggunakan pemangkin meningkat daripada 20.5 kepada 37.8 cP. Kalsium oksida memberi kesan pada pengeluaran minyak-bio dari segi kuantiti dan kualiti. Analisa morfologi permukaan pemangkin menunjukkan kelompok kemas, bijian berliang dan permukaan seragam. Komposisi pemangkin adalah 3.0% C, 40.1% O₂ dan 56.9 % Ca. Komposisi utama pemangkin adalah kalsium oksida iaitu sebanyak 98.5%. Luas permukaan pemangkin kulit kerang terkalsin, saiz liang dan isi padu liang masing-masing adalah 10.2187m² g⁻¹, 122.918Å dan 0.03421cm³ g⁻¹. Oleh itu, sisa kulit kerang yang kaya dengan elemen kalsium sesuai sebagai pemangkin yang murah dan teknologi hijau bagi penghasilan minyak-bio daripada sisa kepada kekayaan.

Waste Seahell as Calcium Oxide Catalyst for Bio-oil Production from Empty Fruit Bunch

ABSTRACT

Oil palm waste could be converted into bio-oil through pyrolytic process due to its renewable resource to ensure continuity and capacity for renewable-energy solution. It is a great challenge to convert empty fruit bunch (EFB) into liquid product which is bio-oil in an effective way. In addition, catalyst was added in the pyrolysis process to evaluate the effect of catalytic pyrolysis EFB towards the yields of bio-oil, biochar and gas as pyrolysis product yields. Therefore, this study was conducted to evaluate the effect of waste seashell based calcium oxide (CaO) as catalyst using a fixed bed reactor for bio-oil production from EFB. The optimization process parameters such as particle size (A) pyrolysis temperature (B) and nitrogen flow rate (C) were investigated through central composite design (CCD) with bio-oil considered as the response. The pyrolysis temperature (B) was considered as the most significant parameter followed by particle size (A). From the optimization study, an optimum pyrolysis temperature of 628 °C, nitrogen flow rate of 250 ml/min and the particle size of 710-1000 μm produced 44.1% of bio-oil. The functional group analysis showed the presence of acid, ketone, polycyclic aromatic hydrocarbons (PAHs), alcohol and carbonyl groups. The pH of bio-oil obtained from the catalytic process was higher than the non-catalytic process which varies from pH 3.5 to pH 4.3. Therefore the acidity of bio-oil was reduced in presence of CaO catalyst from seashell. The effect of viscosity of bio-oil obtained by catalytic process was also enhanced from 20.5 to 37.8 cP. Therefore, CaO catalyst from waste seashell affected the production of bio-oil in terms of quantity and quality. Morphological analysis of catalyst from waste seashell showed well organized, porous grains with uniform surface. The compositions of catalyst were 3.0 % C, 40.1 % O₂ and 56.9 % Ca, and total composition of the catalyst was 98.5 %. The surface area of the calcined seashell catalyst, pore size and pore volume were 10.22 m²g⁻¹, 122.92 Å and 0.0341 cm³g⁻¹ respectively. Therefore, calcined waste seashell as calcium oxide catalyst is rich in calcium suitable as a catalyst which is very cost effective and green technology for the production of bio-oil from waste to wealth.

CHAPTER 1

INTRODUCTION

1.1 Background of Study

The global productions of biomass are enormous and different types of biomass are used all over the world for energy generation. Biomass provides a clean, renewable-energy source that could improve the environment, economy and energy security. The use of these waste materials will depend on a knowledge, economics and technologies that are used to transform them into manageable products (Sukiran, 2009) Biomass can be converted into liquid by thermochemical and biochemical techniques (Badalai & Mahanta, 2015). In biochemical technique, the biomass conversion includes metabolic action of organism or bacteria. The thermochemical conversion of biomass includes combustion, gasification, liquefaction, pyrolysis and carbonization that can be used to convert the biomass into the energy which will yield range of products such as solid, gas or liquid. Pyrolysis is a well-known technology of biomass conversion into gaseous form with application of heat in oxygen free condition. The vapour produced during pyrolysis, can be converted into liquid by condensing this vapour which is known as bio-oil. Therefore, pyrolysis of biomass has gained attention because it can produce liquid which can yield up to 75% wt. on a dry feed (Abnisa, et al., 2011). In many applications, which include boilers, furnace, engines and turbines, to generate electricity, bio-oil can be substituted as fuel oil and diesel. Besides, various chemicals such as acetic acid, food flavorings, preservatives adhesive, hydrogen and sugars can be purified using bio-oil that serve as extractant (Chan et al., 2014).

1.2 Problem Statement

Bio-oil is a key ingredient in the energy substituent and chemical feedstock but the effective use of bio-oil is restricted due to its poor quality. Bio-oil derived from pyrolysis of biomass can be highly oxygenated, viscous, corrosive, relatively unstable and chemically very complex. The present of oxygen in the bio-oil has negative effect such as further increasing the corrosion due to its low pH. Upgrading the bio-oil by catalytic pyrolysis has received increasing consideration and the catalyst is expected to improve the yield and the quality of bio-oil. However, there are several drawbacks associated with this such as current practices which focus on the utilization of synthesized acidic or basic metal oxides. To date no work was done on utilization of waste seashell as catalyst in catalytic pyrolysis of EFB in fixed bed reactor.

1.3 Objective of the Study

The general objective of this research is to evaluate the catalytic pyrolysis of empty fruit bunch (EFB) with waste seashell in fixed bed reactor towards the distribution of product yields and composition of bio-oil obtained via non-catalytic and catalytic pyrolysis process. The specific objectives are as follows:

1. To optimize the effect of pyrolysis parameters of EFB such as pyrolysis temperature, particle size and nitrogen flow rate by central composite design (CCD) in fixed bed reactor.
2. To characterize the catalyst CaO from waste seashell and the pyrolysed bio-oil.
3. To evaluate the effect of waste seashell catalyst in the pyrolysis process.

1.4 Hypothesis

In this study, the effect of the pyrolysis parameter such as pyrolysis temperature, particle size and nitrogen flow rate on bio-oil production were investigated and then to obtain these parameters were systematically varied to maximize bio-oil yield in optimum pyrolysis condition. The waste seashell catalyst can be used in pyrolysis process as catalyst in the pyrolysis of EFB that improve towards the distribution of pyrolysis product yields. The physio chemical properties of bio-oil obtained were also evaluated.

1.5 Scope of the Study

The scope of the research is to use waste seashell as catalyst in pyrolysis process of EFB in the production of bio-oil. The surface morphological, chemical composition and surface area of the catalyst were characterized. The pyrolysis process is carried out in the fixed bed reactor. The influence of particle size, pyrolysis temperature and nitrogen sweep gas flow rate across the bed on the bio-oil yield were investigated. Design of experiment (DoE) is employed to investigate the effect of pyrolysis parameters for the production of bio-oil. A standard response surface methodology (RSM) analysis in conjunction with CCD is utilized to develop experimental runs. The optimization method of central composite design (CCD) is used to optimize the parameters (Mohamed et al., 2014). Comparative study on the effectiveness of the calcium oxide waste seashell catalyst and the commercial catalyst which zinc oxide used in bio-oil production are determined. Bio-oil is collected and analysed. Biochar produced as by-product is measured and the gas by-product is vented out as it passed through the condenser. The

physical and chemical properties of the bio-oil such as viscosity, pH value, functional groups and chemical compounds of bio-oil produced are identified.

©This item is protected by original copyright

CHAPTER 2

LITERATURE REVIEW

2.1 Pyrolysis

Pyrolysis is defined as thermochemical conversion of organic material or biomass in the absence of oxygen to produce biochar, bio-oil and gas mixture (Yaman, 2004). Pyrolysis is derived from Greek words *pyro* means fire and *lysis* means decomposition or breaking down a complex mass into constituent parts at high temperature. During the pyrolysis process, complex macromolecules of biomass decompose into relatively smaller molecule producing three distinguishable products. The products are biochar comprised of carbon and ash, a mixture of gases which is mainly of carbon monoxide (CO), methane (CH₄), ethane (C₂H₆), ethylene (C₂H₄) and hydrogen (H₂) and bio-oil which consists of oxygenates, aromatic, water, low degree of polymerization product, and tar (Kantarelis, 2014).

Pyrolysis is an endothermic process and requires an external heat source. During pyrolysis organic compounds are distilled and vaporized to form combustible gas, by heating them in oxygen free atmosphere. The energy is necessary for driving this process, including the energy required to raise the biomass from room temperature to the reaction one (sensible energy) and the energy to convert the original biomass into the pyrolysis products (reaction enthalpy). The heat demand can be supplied by different heat sources: (i) burning an auxiliary fuel, (ii) burning the gas and/or solid fraction obtained in the process, (iii) electric heating, and (iv) hot

sand or molten salts (Luo & Feng, 2017). Heat for the process can be provided by partial combustion of pyrolysis gas within the furnace and combustible elemental carbon. The oxidized portion of combustible gas may be used as fuel in external combustion chamber with resulting energy recovery by conventional waste-heat-boiler technology. Carbon levels in the furnace are higher for pyrolysis than normal incineration (Forbes et al., 2008). Waste heat is an alternative energy source for the pyrolysis processes, which facilitates energy conservation. Zhao et al., (2010) investigated that the combustible gases production from municipal solid waste using hot blast furnace slag as the heat carrier in a fixed-bed reactor.

2.1.1 Different Types of Pyrolysis

Pyrolysis can be divided into three main categories which are differentiated by pyrolysis temperature, heating rate, solid residence time and biomass particle size. The three types of pyrolysis are slow pyrolysis, fast pyrolysis and flash pyrolysis. The processes vary from each other in terms of chemistry, overall products and quality of yields (Jahirul, et al., 2012).

Slow pyrolysis is generally conducted to enhance biochar and syngas production at low temperature with a low heating rate at 0.1-1°C/s. In contrast, the fast pyrolysis is generally used for production of bio-oil at high heating rate between 10-200°C/s. This process or condition will generate high yield of bio-oil production and a small amount of biochar. As for flash pyrolysis, it needs a high heating rate of more than 1000°C/s, a very short residence time and small particle size which is less than 0.2 mm in order to reduce internal heat transfer limitation (Marshall, 2013). Table 2.1 represents the summary of types of pyrolysis.