



Effect of Heat Treatment on Hardness and Wear Properties of an Aluminum Alloy of Motorcycle Piston

by

Mohd Fizam bin Hj Zainon

0731410173

A thesis submitted

In fulfilment of the requirement for the degree of
Master of Science (Mechanical Engineering)

**School of Mechatronics Engineering
Universiti Malaysia Perlis**

2010

ACKNOWLEDGEMENTS

By the name of Allah, The Most Gracious and The Most Merciful, all the praise belongs to Allah, The Most Beneficent and Magnificent, Who provided me the courage and persistence to conclude this work with successful completion, Who was with me in the most difficult times and always. I thank Almighty for blessing me with an opportunity to get admittance in School of Mechatronics Engineering, Universiti Malaysia Perlis. My gratitude is also due to the esteemed University and to its learned school members for imparting quality learning and knowledge with their valuable support and guidance that had led my way through this point of undertaking my thesis work.

My profound appreciation and heartfelt gratitude go to my thesis advisor Dr. Khairul Rafezi bin Ahmad, Dean, School of Materials Engineering for his constant endeavour, guidance and the numerous moments of attention, he devoted throughout of this research work. I extend my appreciation to my thesis advisor members Mr. Ruhiyuddin bin Mohd Zaki and Mr. Ruslizam bin Daud for their constructive and positive criticism, extraordinary attention and through provoking association in my thesis work. I would like to acknowledge Materials School staff members specially Dr Mazlee bin Md Noor and Mr. Shaiful Rizam bin Samsudin and Materials Lab staff for their cooperation in carrying out this work.

I would also like to take this opportunity to thank my father Haji Zainon bin Man, mother Hajjah Fatimah binti Jaafar, brothers and sister for their

continuous supports and understanding. Last and very important for all is acknowledgement to the understanding, sacrifice, encouragement and moral support from my wife Norsiah bt Hj Ashaari, my sons Muhammad Aliff Naif and Muhammad Aidil Nafis and my daughters Nurin Awatif and Naufal Afrina. I am very much indebted especially to my wife for her support and enormous sacrifice and her confidence in me.

© This item is protected by original copyright

TABLE OF CONTENT

Acknowledgements	ii
Table of Content	iv
List of Table	x
List of Figure	xiv
List of Abbreviations	xix
List of Symbols	xxii
List of Conference and Publications	xxiii
Abstrak	xxiv
Abstract	xxv

CHAPTER 1

INTRODUCTION

1.0	Introduction	1
1.1	Background of the Research	2
1.2	Researcher Review	3
1.3	Problem Statement	4
1.4	Significance of the Study	6

1.5	Objective.....	7
1.6	Scope	7

CHAPTER 2

LITERATURE REVIEW

2.0	Aluminum.....	8
2.1	Aluminum Alloy.....	10
2.1.1	Wrought Alloys.....	11
2.1.2	Casting Alloys.....	12
2.2	Aluminum – Silicon Alloys.....	15
2.3	Casting Process.....	17
2.4	Aluminum Alloy Piston.....	17
2.4.1	Eutectic, Hypoeutectic and Hypereutectic Piston.....	20
2.4.2	Series.....	21
2.4.3	Chemical Composition.....	22
2.5	Phase Diagram.....	24
2.5.1	Binary Phase Diagram (Al-Si).....	25
2.5.2	Ternary Phase Diagram.....	27
2.5.3	Al-Si-Cu-Mg Phase Diagram.....	28
2.6	Heat Treatment in Aluminum Alloy.....	30
2.6.1	Solution Treatment	33
2.6.2	Quenching.....	37
2.6.3	Aging.....	38

2.6.3.1	Natural Aging.....	39
2.6.3.2	Artificial Aging.....	40
2.6.4	Effect of Aging Time on Strength and Hardness.....	41
2.7	Microstructure Analysis.....	42
2.7.1	Research Review on Microstructure Analysis.....	43
2.8	Hardness Analysis	52
2.8.1	Research Review on Hardness Analysis.....	53
2.9	Wear Analysis.....	57
2.9.1	Type of Wear Mechanism.....	58
2.9.2	Wear and Friction Measurement	60
2.9.3	Wear Rate	61
2.9.4	Research Review on Wear Analysis.....	62

CHAPTER 3

MATERIALS AND METHODS

3.0	Introduction.....	66
3.1	Experimental Methods.....	67
3.2	Sample Sampling.....	68
3.3	Heat Treatment of the Sample.....	70
3.4	Sample Preparation.....	71
3.5	Microstructure Analysis.....	72
3.6	Hardness Analysis.....	73
3.7	Wear Analysis	74

CHAPTER 4

RESULTS AND DISCUSSIONS

4.0	Introduction.....	77
4.1	Raw Materials Analysis (As Received).....	78
4.1.1	Chemical Composition.....	80
4.1.2	Microstructure.....	83
4.1.2.1	NPS and NPH Samples (New Pistons).....	84
4.1.2.2	UPS and UPH Samples (Used Piston).....	86
4.1.3	Mechanical Properties.....	87
4.1.3.1	Hardness: NPS and NPH Samples.....	87
4.1.3.1.1	Hardness: UPS and UPH Samples.....	88
4.1.3.2	Wear.....	90
4.1.3.2.1	NPS and NPH Samples.....	91
4.1.3.2.1.1	Worn Surface: NPS and NPH Samples.....	95
4.1.3.2.2	UPS and UPH Samples.....	98
4.1.3.2.2.1	Worn Surface: UPS and UPH Samples.....	102
4.2	Solution Treatment.....	104
4.2.1	Effect on Microstructure.....	105
4.2.2	Effect on Mechanical Properties.....	107
4.2.2.1	Hardness.....	107
4.2.2.2	Wear.....	109
4.2.2.2.1	Worn Surface.....	114
4.3	Aging.....	116
4.3.1	Effect on Microstructure.....	117

4.3.1.1	NPS – Aging at 130°C	117
4.3.1.2	NPS – Aging at 170°C	120
4.3.1.3	NPS – Aging at 210°C	123
4.3.1.4	NPH – Aging at 130°C	125
4.3.1.5	NPH – Aging at 170°C	127
4.3.1.6	NPH – Aging at 210°C	129
4.3.2	Effect on Mechanical Properties	131
4.3.2.1	Hardness	131
4.3.2.1.1.	NPS – Aging	131
4.3.2.1.2.	NPH – Aging	134
4.3.2.2	Wear	137
4.3.2.2.1.	NPS – Aging	138
4.3.2.2.2.	NPH – Aging	144
4.3.2.2.3.	Worn Surface	152
4.3.2.2.4.	Characteristic of Counterface Wear	158
4.3.2.2.5.	Characteristic of Debris	159

CHAPTER 5

CONCLUSIONS AND RECOMMENDATIONS

5.0	Conclusions	162
5.1	Recommendation for Future Research	163

REFERENCE.....	165
----------------	-----

APPENDICES

A. Mechanical Properties Data.....	171
B. Standard Setting.....	172
C. Hardness Raw Data: As Received.....	173
D. Hardness Raw Data: UPS and UPH Samples.....	174
E. Wear Raw Data: As Received.....	175
F. Wear Raw Data: UPS and UPH Samples.....	176
G. Hardness Raw Data: Solution Treatment.....	179
H. Wear Raw Data: Solution Treatment.....	180
I. Hardness Raw Data: NPS – Aging.....	181
J. Hardness Raw Data: NPH – Aging.....	183
K. Wear Raw Data: NPS – Aging.....	185
L. Wear Raw Data: NPH – Aging.....	187

LIST OF TABLE

Table

2.1	Wrought Alloy Designation System	12
2.2	Casting Alloy Designation System.....	13
2.3	Chemical Compositions of Some Commercial Al-Si-Cu-Mg Alloys	23
2.4	Chemical Composition Value for AA 332.0 Series.....	24
2.5	Chemical Composition and Density of Phases Formed In the Al-Cu-Fe-Mg-Ni-Si System.....	29
2.6	Invariant Reactions in Constituent Quaternary	30
	Systems of the Al-Cu-Fe-Mg-Ni-Si System	
2.7	The Precipitation Process in Aluminium Alloys (Al-Mg-Si).....	32
2.8	Solution Treatment and Aging Data.....	35
2.9	Recommended Solution treatment for.....	36
	Cast Alloys (sand and permanent mould type)...	
2.10	Chemical Composition in AA-6013 and AA-6061.....	53
2.11	Chemical Composition (wt%) of.....	54
	Aluminum-Based Piston Alloy	

3.1	Samples Name and Description	68
3.2	Keller's Reagent Composition	72
4.1	Chemical Composition (wt %) of the As Received	81
4.2	Chemical Composition for AA332.0 Series Alloys	82
4.3	NPS – Aging Microhardness (H_V) Data	131
4.4	NPH – Aging Microhardness (H_V) Data	134
Appendix A		
A. 1	Aluminum Alloy 3xx.x Series	171
Appendix B		
B. 1	Setting for Image J Software	172
Appendix C		
C. 1	As Received (NPS and NPH)	173
Appendix D		
D. 1	UPS Samples	174
D. 2	UPH Samples	174

Appendix E

E. 1	Wear Data for As Received	175
------	---------------------------------	-----

Appendix F

F. 1	Wear Data for UPH – 15k	176
F. 2	Wear Data for UPH – 40k	177
F. 3	Wear Data for UPS – 15k	177
F. 4	Wear Data for UPS – 40k	178

Appendix G

G.1	Hardness Data for Solution Treatment (NPS and NPH)	179
-----	--	-----

Appendix H

H. 1	Wear Data for Solution Treatment NPS	180
H. 2	Wear Data for Solution Treatment NPH	180

Appendix I

I. 1	Hardness Data for NPS - 130 ⁰ C	181
I. 2	Hardness Data for NPS - 170 ⁰ C	181
I. 3	Hardness Data for NPS - 210 ⁰ C	182

Appendix J

J. 1	Hardness Data for NPH - 130 ⁰ C	183
J. 2	Hardness Data for NPH - 170 ⁰ C	183
J. 3	Hardness Data for NPH - 210 ⁰ C	184

Appendix K

K. 1	Wear Data for NPS - 130 ⁰ C/5h.....	185
K. 2	Wear Data for NPS - 170 ⁰ C/2h.....	186
K. 3	Wear Data for NPS - 210 ⁰ C/2h.....	186

Appendix L

L. 1	Wear Data for NPH - 130 ⁰ C/3h.....	187
L. 2	Wear Data for NPS - 170 ⁰ C/2h.....	187
L. 3	Wear Data for NPS - 210 ⁰ C/2h.....	188

© This item is protected by original copyright

LIST OF FIGURE

Figure

2.1	The Density of the Molten Aluminium with Purity 99.996%	9
2.2	Processing of Aluminium Alloys	11
2.3	The Principal Groups of Aluminium Alloys	14
2.4	Piston Terminology	18
2.5	Temperature Distribution at Piston	19
2.6	Al-Si Binary Phase Diagram	26
2.7	Ternary Phase Diagrams (Vertical Section)	27
2.8	Ternary Phase Diagrams (Horizontal Section)	27
2.9	Line Diagram of Stable Equilibrium Phase Fields in Al-Mg-Si-Cu System at Normal Aging Temperatures	28
2.10	A Fine Dispersion of Elements and Compounds	38
2.11	Schematic Aging Curve at a Particular Temperature For A Precipitation Hardenable Alloy	41
2.12	Optical Micrograph of Al-12%Si	43
2.13	Optical Micrograph of Hypereutectic Alloy (A390.0) And Eutectic Alloy (A384.0)	45

2.14	Microstructures of Eutectic Alloy	46
2.15	Optical Micrograph of Al - 7%Si - 3.5%Cu Alloy	47
2.16	Optical Micrograph of The β -Platelets Structure	48
2.17	Optical Micrograph of Al – Si Piston Alloys.....	49
2.18	Microstructure of 0.6 wt%Si After Heat Treatment.....	50
2.19	Microstructure of 319 Alloys.....	51
2.20	Microstructure of A332.0 Alloys Series.....	51
2.21	Hardness vs Aging for AA-6013	54
2.22	Hardness Value for the Al – Si Piston Alloys.....	55
2.23	Effect of Aging Temperature on the..... Hardness of 356 and 319 Alloy	56
2.24	Wear Rate vs. Sliding Distance.....	63
2.25	Volume Loss and Friction Coefficient of..... Hypereutectic Al – Si – Cu Alloys Sliding at 10 N	64
3.1	Brief Outline of Experiment.....	67
3.2	Sample Selection Process and Data Collection Framework.....	69
3.3	Heat Treatment Profile.....	70
3.4	Cold Mounting Samples.....	71

3.5	Optical Microscope Equipped with Digital Camera.....	73
3.6	Wear Apparatus	75
4.1	Brief Outline of Chapter 4.....	78
4.2	Piston Dimension and Terminology.....	79
4.3	Optical Micrograph of As Received	84
4.4	Optical Micrograph of UPS and UPH	86
4.5	Microhardness of As Received	88
4.6	Effect of Mileage on the Microhardness	89
	of UPS and UPH	
4.7	As Received: Volume Loss vs. Sliding Distance	91
4.8	As Received: Wear Rate vs. Sliding Distance	93
4.9	As Received: Wear Coefficient vs. Sliding Distance.....	94
4.10	Optical Photographs of Worn Surface (As Received).....	96
4.11	UPS and UPH: Volume Loss vs. Sliding Distance	98
4.12	UPS and UPH: Wear Rate vs. Sliding Distance	99
4.13	UPS and UPH: Wear Coefficient vs. Sliding Distance.....	101
4.14	Optical Micrographs of Worn Surface (UPS and UPH)	103
4.15	Optical Micrograph of Solution Treatment.....	105

4.16	Microhardness of Solution Treatment.....	108
4.17	Solution Treatment: Volume Loss vs. Sliding Distance.....	109
4.18	Solution Treatment: Wear Rate vs. Sliding Distance.....	111
4.19	Solution Treatment: Wear Coefficient vs. Sliding Distance.....	113
4.20	Optical Micrographs of Worn Surface (Solution Treatment).....	114
4.21	Optical Micrograph of NPS - 130°C.....	118
4.22	Optical Micrograph of NPS - 170°C.....	121
4.23	Optical Micrograph of NPS - 210°C.....	123
4.24	Optical Micrograph of NPH - 130°C.....	125
4.25	Optical Micrograph of NPH - 170°C.....	127
4.26	Optical Micrograph of NPH - 210°C.....	130
4.27	Effect of Aging on Microhardness at NPS.....	132
4.28	Effect of Aging on Microhardness at NPH.....	135
4.29	NPS – Aging: Volume Loss vs. Sliding Distance.....	138
4.30	NPS – Aging: Wear Rate vs. Sliding Distance.....	140
4.31	NPS – Aging: Wear Coefficient vs. Sliding Distance.....	142
4.32	NPH – Aging: Volume Loss vs. Sliding Distance.....	145
4.33	NPH – Aging: Wear Rate vs. Sliding Distance.....	147

4.34	NPH – Aging: Wear Coefficient vs. Sliding Distance.....	150
4.35	Optical Micrographs of Worn Surface (NPS – Aging).....	153
4.36	Optical Micrographs of Worn Surface (NPH – Aging).....	155
4.37	SEM Micrographs of Worn Surface of Sleeve (Counterface)	158
4.38	SEM Micrographs of Wear Debris.....	160
4.39	Delaminated Wear Debris Particles.....	161

© This item is protected by original copyright

LIST OF ABBREVIATIONS

AA 2xx.x	Aluminum Alloys Series 2000
AA 3xx.x	Aluminum Alloys Series 3000
AA 4xx.x	Aluminum Alloys Series 4000
AA	Aluminum Alloy
Al	Aluminum
Al ₂ Cu	Aluminum Copper
Al-Si	Aluminum Silicon
ASTM	American Standard Testing Materials
Cu	Copper
EDS	Energy Dispersive X-Ray Spectroscopy
Fe	Iron
g/cm ³	Gram per Centimeter Cubic
GPa	Giga Pascal
h	Hours
HF	Hydrofluoric Acid
H _v	Vickers hardness value
K	Wear Coefficient

kg/cm ³	Kilogram per Centimeter Cubic
kg/m ³	Kilogram per Meter Cubic
km	Kilometre
kN	Kilo Newton
L	Liquid
Mg ₂ Si	Magnesium Silicide
mm ³ /min	Milimeter Cubic per Minute
MODENAS	Motosikal dan Enjin Nasional
MPa	Mega Pascal
N/m ²	Newton per Meter Square
NASA	National Aeronautics & Space Administration
Ni	Nickel
NPH	New Piston Head
NPS	New Piston Sidewall
P	Phosphorus
Q	Quaternary Intermediate Phase
rps	Revolutions per Second
SEM	Scanning Electron Microscope
Si	Silicon

SiC	Silicon Carbide
UPH	Used Piston Head
UPS	Used Piston Sidewall
V	Vanadium
Zn	Zink

© This item is protected by original copyright

LIST OF SYMBOLS

%wt Weight Percent

μm Micron

$^{\circ}\text{C}$ Degree Celsius

E Modulus Young

N/m^2 Newton per Meter Square

δ Delta

ϵ Epsilon

θ Theta

LIST OF CONFERENCE AND PUBLICATIONS

1. **M.Z. Fizam¹**, K.A. Rafezi², M.Z. Ruhiyuddin², D. Ruslizam¹” *Effect of Heat Treatment on Aluminum Alloy: A Study of Motorcycle Piston*”. Engineering Postgraduate Conference (2009).
2. **M.Z. Fizam¹**, K.A. Rafezi², M.Z. Ruhiyuddin², D. Ruslizam¹” *Effect of Age Hardening on Aluminum Alloy: A Study of Motorcycle Piston*”. Malaysian Metallurgical Conference (2009).

© This item is protected by original copyright

Abstrak

Kajian dilakukan untuk menyelidik kesan rawatan haba terhadap mikrostruktur, kekerasan dan haus omboh aloi aluminium dan juga bertujuan meningkatkan sifat kekerasan dan ketahanan haus bagi omboh aloi aluminium melalui kaedah perawatan haba. Bahan ujikaji terdiri daripada omboh aloi aluminium yang dihasilkan oleh sebuah syarikat pengeluar omboh dan digunakan oleh enjin empat lejang "Motosikal Nasional". Unsur – unsur aloian seperti Al, Si, Cu, Mg, Ni dan Fe dikesan pada sampel asal dengan 8% kandungan silika. Rawatan larutan dilakukan pada suhu 500°C selama 5 jam dan dilindap kejut di dalam air pada suhu bilik. Rawatan penuaan dilakukan pada suhu 130°C, 170°C dan 210°C untuk tempoh 1 hingga 6 jam bagi pemerhatian kesan penuaan ke atas sifat mekanikal dan mikrostruktur. Analisis mikrostruktur dijalankan dengan menggunakan mikroskop optik dilengkapi dengan kamera digital dan Mikroskop Elektron Imbasan (SEM). Pengukuran kekerasan dijalankan dengan menggunakan penguji mikrokekerasan Vickers. Ujian gelongsor kering telah dijalankan dengan menggunakan kaedah ujikaji pin di atas cakera. Kehilangan isipadu, kadar haus dan pekali haus di nilai melalui kaedah tanpa pelinciran dengan pemberat 10 N, kelajuan gelongsor 1.0 m/s, dan jarak gelongsoran 0.1, 0.25, 0.5, 1 dan 2 km. Keputusan menunjukkan, selepas rawatan haba lengkap, mikrostruktur didapati mempunyai mendakan lebih keras seperti $\text{Al}_6\text{Cu}_3\text{Ni}$, β (Al_5FeSi) dan Mg_2Si . Di dapati struktur zarah silika berbentuk plat asikular (bentuk bulat). Keputusan mikrokekerasan pada sampel penuaan 130°C menunjukkan kenaikan di antara 12.67% hingga 34% berbanding dengan sampel asal. Sementara itu, mikrokekerasan untuk sampel penuaan 170°C menunjukkan peningkatan dari 28.06% hingga 46% dan sampel penuaan 210°C turut menunjukkan peningkatan di antara 25.29% hingga 44.36%. Ujian haus untuk sampel penuaan menunjukkan penurunan kadar haus diantara 14.01% hingga 56.63% apabila dibandingkan dengan sampel asal. Selain itu, nilai pekali haus untuk sampel yang ditua turut menurun di antara 3.09% hingga 42.15% daripada sampel asal. Keputusan daripada pemerhatian menunjukkan sampel penuaan pada 170°C bagi tempoh penuaan 2 jam telah meningkatkan sifat kekerasan dan ketahanan haus pada omboh aloi aluminium.